



# HSM Wire International, Inc

Ph: 330-244-8501 Fax: 330-244-8561

[www.hsmwire.com](http://www.hsmwire.com)

## Fluorinated Ethylene Propylene (FEP), Molded/Extruded

Optical Properties	Metric	English
Transmission, Visable	92.0 - 95.0 %	92.0 - 95.0 %
IR Transmittance	95.0 - 98.0 %	95.0 - 98.0 %
UV Transmittance	91.0 - 92.0 %	91.0 - 92.0 %

Some of the values displayed may have been converted from their original units and/or rounded in order to display the information in a consistant format.

\*To be used as a guideline only

Copyright HSM Wire International 2013

Rev 1.06.14.13